MOTIP Sprej za brtvljenje

Tehnički list



Sredstvo MOTIP Sealing Spray je fleksibilni premaz jednostavan za uporabu za brtvljenje i popunjavanje malih propuštanja i pukotina. Zadržava fleksibilnost čak i pri temperaturnim promjenama i prikladno je za uporabu na različitim podlogama, poput metala, plastike, PVC-a, betona i vinila. Sprej za brtvljenje može se koristiti u zatvorenom i na otvorenom i stoga je idealan za brtvljenje malih propuštanja i pukotina na olucima, ventilacijama, odvodima i slično. Sredstvo MOTIP Sealing Spray otporno je na vremenske utjecaje, UV zračenje i može se premazivati različitim sustavima boja.

Šifra: 07307, 07308, 07309

Kvaliteta i svojstva

Vodootporno.
Fleksibilno
Visoka svojstva punjenja
Otporno na vremenske utjecaje i UV zračenje
Može se premazivati različitim sustavima boja
Jednostavno za uporabu
Za unutarnju i vanjsku uporabu

Fizikalni i kemijski podaci

Baza: Sintetička smola
Naziv boje:
- black
- grey
- white

Mirisati: Karakterističan
Stupanj sjajai: szőnyeg, 10 ±2
Suha prašina: 10 - 20 min
Suho na dodir: 20 - 30 min
Može se premazati: 24 h
Površine: Metal, plastic, PVC, concrete, vinyl
Minimalna radna temperatura: 10 °C
Maksimalna radna temperatura: 25 °C
Flash point: n.a.
Stabilnost skladištenja: 10 y
Sadržaj: 500 ML

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com

Upute za korištenje

Prije uporabe, pažljivo pročitajte upute na pakiranju i postupite u skladu s njima.
Površina mora biti čista, suha i odmašćena. Uklonite labavi stari lak i hrđu te lagano izbrusite površinu. Ponovno očistite i osušite površinu.
Aerosol treba imati sobnu temperaturu. Najbolja temperatura obrade je od 10 do 25 °C.
Prije uporabe, protresite aerosol 2 minute i poprskajte uzorak. Udaljenost od površine koja će se tretirati treba biti oko 25 do 30 centimetara.
Nanesite prvi sloj i pustite da se suši približno 20 do 25 minuta.
Zatim nanesite drugi sloj, pustite da se suši 5 minuta i provjerite je li površina zabrtvljena. Ako nije, nanesite još jedan sloj. Prije nanošenja sljedećeg sloja, ponovno protresite aerosol. Dopustite vrijeme sušenja od 5 minuta između različitih slojeva.
Nakon uporabe, očistite ventil (okrenite aerosol naopako i pritisnite mlaznicu otprilike 5 sekundi).
Vrijeme sušenja ovisi o temperaturi okoline, vlažnosti zraka i debljini nanesenog sloja.

Environmentally sound

European Aerosols is committed to apply formulations without restricted or critical ingredients and to achieve best possible performance. The caps and packagings are made of recyclable material.

Disposal

Only the completely emptied cans should be put into the recycling skip or appropriate container for reclaimable refuse. Cans which are not empty should be disposed off as “special refuse”.

Marking/Labelling

All products made by European Aerosols comply with the actual labelling regulations according to Preparation Guideline 1999/45/EG. All aerosols correspond to TRGS 200 and TRG 300 as well as to aerosol guideline 75/324/EWG in the actually valid version.

As of August 5, 2025 – This release replaces all eventually earlier issued versions.

European Aerosols GmbH, Kurt-Vogelsang-Straße 6, 74855 Haßmersheim – info-de@european-aerosols.com
European Aerosols B.V., Wolfraamweg 2, NL-8471 XC Wolvega – info-nl@european-aerosols.com