## Valtti Puuöljy Akva (Wood Oil Akva)

**Description** Water-borne wood oil emulsion based on vegetable oils.



Suitable for oiling of exterior wood surfaces, also for hardwood, **Product features** 

impregnated and heat treated wood as well as untreated wood. Garden furniture, terraces, stairs, fences, railings, jetties, doors.

Recommended

uses

## **TECHNICAL DATA**





Base paints

Colour Range Colourless. Semi-transparent Wood Finishes colour card.

Colour Cards Semi-transparent Wood Finishes Colour Card

undefined Gloss grade

 $5-7 \text{ m}^2/\text{I}$  depending on the porosity of the surface. Coverage

Can sizes 0.9 I and 2.7 I

Thinner Water

Application method Brush or sponge.

Drying time at 23°C and 50% relative air humidity

Touch-dry after a few hours under normal conditions. The porosity of the substrate and the amount of oil used affect the drying time. The second coat can be applied as soon as the oil is absorbed into wood or the surface is dry, normally approx. after 24 hours

Weather resistance Check the condition of the oiled wood annually and treat with oil if necessary.

16 %. Solids volume

Density 1.0 kg/l, ISO 2811.

Keep from freezing. Badly closed or short cans and/or tinted products do not Storage

withstand long storage. Tinted products should be used during the same painting

season.

Product code 256 0070

## **APPLICATION DETAILS**

Application conditions

The surface to be treated must be dry, the temperature of the air at least +5 ?C , and

the relative humidity of the air below 80% during painting and drying.

Preparation

Remove dirt, dust and loose material from the wood surface. If previously treated surfaces have faded of there is mould on them, wash down the surfaces with Homeenpoisto (Mould Removal) or with Tehopesu (Power Cleaner) according to

instructions.

Treatment

Stir Valtti Wood Oil Akva thoroughly before use and from time to time during application. Apply 1 to 2 coats by brush or sponge. Spread evenly in continuous strokes to avoid overlapping. Wipe off excess oil within 30 min, as the oil should not form a film on the wood. The second coat can be applied as soon as the oil is absorbed or the surface is dry, normally after 24 hours. Tinted wood oil (application 2 times) is recommended for a more intensive colour . Oil treatment makes the wood

look darker. Treat surfaces once a year if necessary.

Cleaning of tools

Wash the tools with soap and water or Tikkurila Pensselipesu (Tool Cleaner).

**HEALTH AND SAFETY CLASSIFICATION** 

> Contains cobalt compound. May produce an allergic reaction A Material Safety Data Sheet is available on request.



Material Safety Data Sheet - VALTTI Wood Oil Akva

**PROTECTION AND WASTE DISPOSAL** 

**ENVIRONMENTAL** Empty cans should be recycled or disposed of in accordance with local regulations. Liquid waste should be destroyed according to the local

regulations.

**TRANSPORT** VAK/ADR -

mli171106/lko191106/akk221206/256 0070

The above information, based on laboratory tests and practical experience, has been proved valid at the date marked on the product data sheet. The quality of the product is ensured by our operational system, based on the requirements of ISO 9001 and ISO 14001. As a manufacturer we cannot be responsible for any damages caused by using the product against our instructions or for inappropriate purposes.